

Test Report

Report No: E1402072-727 **Date:** 13.03.2014

Company Name: Renco Kompozit Teknolojileri San. Ve Tic. A.Ş.
Address: Hadımköy Yolu Akçaburgaz Mah. 167.Sk. No:7
Kıraç – Esenyurt / İstanbul

Contact Person: Levet İdrisoğlu

Laboratory Receipt Date: 20.02.2014

Sample Description: 4 Unit of 20x20 cm Naturel (White) Composite Test Plates

Test Results:**Breaking Strength for Composite Plates**

Standard: PFI Metot
Test Date: 27.02.2014

Parameter	Unit	Result	Requirement	Assessment	
				Pass	Fail
Breaking force, average	N	455,05			
Number of test sample		12			
Width of the sample	mm	≈25			
Test speed	mm/dk	10			

The sample test is valid only for this report and this report does not substitute "Produce Certificate". Test results solely refer to the items tested. Extracts of the expertise may not be used without written permission by PFI. Remaining materials will be destroyed after 3 months. In individual cases, tests can be carried out by qualified subcontracting laboratories. Test reports without signature and seal are not valid.


Test Report**Report No:** E1402072-727**Date:** 13.03.2014**Effect of Temperatures**

Standard: PFI Metot

Test Date: 25.02-13.03.2014

Parameter	Unit	Result	Requirement	Assessment	
				Pass	Fail
Breaking force, average	N	476,73			
Number of test samples		12			
Width of the sample	mm	≈25			
Standby temperature / time		-35 °C / 168 h. 23°C / 24 h. 70 °C / 168 h. 23°C / 24 h.			
Test speed	mm/dk	10			

The end of the test sample is released during the test.

Laboratory Manager
Makbule Bektaş**General Manager Assistant -**
Yasemin Sözbir

The sample test is valid only for this report and this report does not substitute "Produce Certificate". Test results solely refer to the items tested. Extracts of the expertise may not be used without written permission by PFI. Remaining materials will be destroyed after 3 months. In individual cases, tests can be carried out by qualified subcontracting laboratories. Test reports without signature and seal are not valid.